

Cross-cut test report

Company: **VERNICI EGIDIO MILESI s.p.a. Milano**

Part concerning the sample

Date arrival of sample: 26th April 2006
 Product description: **White pigmented water cycle for external surface IWC8006/TWE287**
 Applied amount: IWC8006 60 g/m², +TWE287 200 g/m², TWE287 196 g/m². TOT: 456 g/m²
 Commercial name: IWC 8006 + TWE 287
 Test unit: Sample in *Picea abies* "Spruce". Prepared in conformity with standard
 Test area: N° 1 from mm 70 x 150 x 20
 Surface: Smooth semimatt. Product applied from CERTO.
 Lot: Unknown





Reference to the standard:	UNI EN ISO 2409
Author:	UNICHIM
Title:	Cross-cut test.

Part concerning the test

Date of the test: **22-06-2006**
 Operator: Enzo Morandi
 Observer: Alessio Degli Innocenti e Marco Fruscoloni
 Laboratory temperature: 22°C. / Humidity: 50%
 Equipment used: Cross Hutch Cutter mod. 295 Erichsen from 2 mm
 Conditioning: Over 168 hours in controlled condition 23°C / 50% U.R.

Products and results			
Sample's name	Spess PV	Level	Observation
White pigmented water IWC 8006 + TWE 287	µm: 173	0	Perfect cut and adherent

Explication The level of this test is opposite to the other test, in fact here 0 is the best, 5 the worse

Technical responsible	Tester	Laboratory's manager	Watcher
			

Attention: this report concerns only the two tested cycles. This report cannot be reduced or modified for any reason.